

CanusaTube™ - PMOF

High shrink, tubular sleeve for flange joints

Product Description




The CanusaTube™ PMOF high shrink tubular sleeve is used for flange joint applications. It is shipped with a release liner which protects the adhesive and a protective skirting to protect against jagged edges.

Equipment List



Propane tank, hose, torch & regulator; Wire brush for surface abrasion; Knife, roller, rags & approved solvent cleanser; Temperature measuring device; Standard safety equipment; gloves, goggles, hard hat, etc

Flame Intensity & Torch Size




Adjust the flame according to outside conditions.

a. Use bluish-yellow flame for low wind, higher temps.

b. Use blue flame for high wind, lower temperatures.

Always aim the torch perpendicular to the pipe and move in a circumferential direction.

Backfilling Trench




Ensure there is adequate work space area around the pipe in the backfilling trench.

Sleeve Preparation




Before joining together the two pipes, slide the CanusaTube™ sleeve at least 1 metre away from the joint area.

Pre-Warm and Drying




Using the torch and a medium flame, pre-warm and dry the entire sleeve width + 25 mm (1") on each side. Take precaution not to damage the rubber flange seal.

Coating Scraping




Using a triangular scraper, clean the edges of the pipeline coating to remove any sharp corners or burrs.

Solvent Cleaning




Clean the polyethylene coating where the adhesive of the sleeve is going to be applied (100 mm on each side) with a grease and lint-free rag soaked in ethan-ol (94% minimum).

Surface Abrasion




Ensure that the pipe is dry before cleaning. Prepare the surface areas to a minimum of St2 / SP2.

Surface Wiping



Using a dry, grease and lint-free rag, wipe clean or air blast the entire sleeve width + 25 mm (1") on each side to remove any foreign contaminants.

Pre-Heat



Pre-heat the surface areas to a minimum of 50°C (122°F). Using a temperature measuring device, ensure that the correct temperature has been reached.

Protective Skirting Installation



Centre the protective skirting over the flange. Using the tape provided, attach the skirting to the flange. Begin wrapping the protective skirting around flange tightly.




Finish wrapping the protective skirting around the flange. Using the supplied tape, firmly attach the protective skirting around the flange.

Release Liner




Centre the sleeve over the flange joint with the weld area facing upwards. If the Flange is not circular, position the weld seam at the minimum radius point. Completely remove both release liners from the adhesive strips.

Sleeve Installation



Using broad strokes, heat the sleeve circumferentially around the pipe starting at the flange joint. Ensure the weld area receives minimal heating. Continue heating from the centre of the sleeve until sleeve recovery is complete around the flange.



In a similar manner, heat and shrink the sleeve on one side of the flange. Repeat for other side. Shrinking has been completed when the adhesive begins to ooze at the sleeve edges all around the circumference.



In order to avoid a channel formation at the step down, the sleeve should be pressed down. Special attention should be given along the circumference between 4 and 8 o'clock positions.




While sleeve is still hot and soft, use a gloved hand or roller to push any trapped air out of the sleeve. The sleeve should be in full contact with the joint, have adhesive flow beyond both sleeve edges, and the backing should not have cracks or holes.

Finger Tip Test



Ensure the sleeve follows the contour of the surface and that there are no cold spots or burning of the sleeve. The edges should be checked for adhesive ooze and lifting by feeling the edges all around the circumference of the sleeve. If there is edge lifting, the edge should be reworked with additional heat.

Do Not Quench



Do not cool sleeve by using water to quench. Please allow the sleeve to cool naturally.

Inspection



Visually inspect the installed sleeve for the following:

- Sleeve is in full contact with the steel joint.
- Adhesive flows beyond both sleeve edges.
- No cracks or holes in sleeve backing.

Backfilling Guidelines

After shrinking is complete, allow the sleeve to cool for 2 hours prior to lowering and backfilling. To prevent damage to the sleeve, use selected backfill material, (no sharp stones or large particles). Otherwise, an extruded polyethylene mesh or other suitable shield should be used.

Storage & Safety Guidelines

To ensure maximum performance, store Canusa products in a dry, ventilated area. Keep products sealed in original cartons and avoid exposure to direct sunlight, rain, snow, dust or other adverse environmental elements. Avoid prolonged storage at temperatures above 35°C (95°F) or below -20°C (-4°F). Product installation should be done in accordance with local health and safety regulations.

These installation instructions are intended as a guide for standard products. Consult your Canusa representative for specific projects or unique applications.

Canusa-CPS A division of Shawcor Ltd.

Head Office

25 Bethridge Road
Toronto, ON, Canada M9W 1M7
Tel: +1 416 743 7111
Fax: +1 416 743 5927

Canada

Dome Tower St. 2200,
333-7th Avenue SW
Calgary, AB, Canada T2P 2Z1
Tel: +1 403 218 8207
Fax: +1 403 264 3649

Americas

5875 N. Sam Houston Pkwy W.,
Suite 200
Houston, TX, USA 77086
Tel: +1 281 886 2350
Fax: +1 281 886 2353

Middle East

Plot # 37-WR43, Sector no.: ICAD III
Musaffah South, PO Box 2621
Abu Dhabi, The United Arab Emirates
Tel: +971 2 204 9800

Europe, Africa & Russia

Dellaertweg 9-E, Gebouw
"Le Carrefour"
2316 WZ Leiden,
The Netherlands (NL)
Tel: +31 71 80 802 70
Fax: +31 71 80 802 71

Asia-Pacific

101 Thomson Road,
#11-03 United Square
307591 Singapore
Tel: +65 6749 8918
Fax: +65 6749 8919

Quality Management system registered to ISO 9001

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the installation guide when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this installation guide is to be used as a guide and is subject to change without notice. This installation guide supersedes all previous installation guides on this product. E&OE

Part No. 99060-053

IG_CanusaTube PMOF_rev013