

# the REGIONAL LEADER In pipe coating solutions.

## PRITEC®

TECHNICAL DATA SHEET

#### PRODUCT DESCRIPTION

PRITEC® is a two-layer anti-corrosion coating designed to protect pipes used in the oil & gas and water & waste water industries. PRITEC'S® side extrusion application method is ideal for coating small and large diameter pipes ranging from 3/4" to 36" in diameter. This coating combines the proven protective qualities of a polyethylene outer coating with a special butyl rubber adhesive.

ADHESIVE COMPONENT PROPERTIES				
Softening Point	ASTM E 28	190° F		
Water Absorption	ASTM D 570	< 0.1 %		
Adhesive		Compounded Butyl Rubber		

### POLYETHYLENE COMPONENT PROPERTIES

Color		Black
Density	ASTM D 1505	> 0.950
Elongation	ASTM D 638	> 600%
Tensile Strength	ASTM D 638	> 2,800 psi
Outdoor Exposure		> 2 years
Hardness, Shore D	ASTM D 2240	> 60

#### PRITEC® COATING SYSTEM PROPERTIES

Operating Temperature		-40°F to +180°F
* Peel Strength	ASTM D 1000	>20 lbs lineal
Field Bending	Arctic Service Equipment	1.9 degrees per pipe dia.
Water Absorption	ASTM D 570	0.06 %
Impact Resistence	ASTM G 14	33.65 in/lbs (10/40 system)
Volume Resistivity	ASTM D 257	10 x 10 <sup>16</sup> Ohm cm
Dielectric Strength	ASTM D 149 @ 73°F	700 Volts / Mil
Cathodic Disbondment	1.5v / 3% / 70°F /24hrs	6 mm radius

<sup>\*</sup> Peel Strength: Pull rate of (12" / minute) or (1" / 5 seconds). Pull position is 180 degrees in relation to the substrate.